

# LOCTITE ABLESTIK CF 3366

March 2019

## PRODUCT DESCRIPTION

LOCTITE ABLESTIK CF 3366 provides the following product characteristics:

|                                      |                                                                                                                                                                                                                                                                                                                                                                                       |
|--------------------------------------|---------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| <b>Technology</b>                    | Epoxy Film                                                                                                                                                                                                                                                                                                                                                                            |
| <b>Appearance</b>                    | Gray Tan                                                                                                                                                                                                                                                                                                                                                                              |
| <b>Cure</b>                          | Heat cure                                                                                                                                                                                                                                                                                                                                                                             |
| <b>Product Benefits</b>              | <ul style="list-style-type: none"> <li>• High adhesion strength at elevated temperatures</li> <li>• High electrical conductivity</li> <li>• High thermal conductivity</li> <li>• Low cure temperature</li> <li>• Custom preforms</li> <li>• Adhesion with flexibility</li> <li>• Uniform bondline adhesion</li> <li>• Void-free bondline</li> <li>• Passes NASA outgassing</li> </ul> |
| <b>Application</b>                   | Assembly                                                                                                                                                                                                                                                                                                                                                                              |
| <b>Filler Type</b>                   | Silver                                                                                                                                                                                                                                                                                                                                                                                |
| <b>Thickness</b>                     | 102µm                                                                                                                                                                                                                                                                                                                                                                                 |
| <b>Substrates</b>                    | Copper, Brass, Kovar and Aluminum                                                                                                                                                                                                                                                                                                                                                     |
| <b>Typical Assembly Applications</b> | Fluoropolymer circuits, Ceramic circuits, Metal backplanes and Heatsinks                                                                                                                                                                                                                                                                                                              |

LOCTITE ABLESTIK CF 3366 film adhesive is formulated for electrical, thermal and mechanical assembly applications. The combination of adhesive properties ensures reliable RF ground plane performance suitable for extreme environmental conditions.

LOCTITE ABLESTIK CF 3366 passes NASA outgassing standards.

## TYPICAL PROPERTIES OF UNCURED MATERIAL

|                                                        |             |
|--------------------------------------------------------|-------------|
| Work Life @ 25°C, days                                 | 91          |
| Shelf Life @ 5°C (from date of manufacture), days      | 183         |
| Peak Exotherm Temperature, DSC, Ramp Rate=10°C/ minute | 165°C ± 5°C |

## TYPICAL CURING PERFORMANCE

### Cure Schedule

60 minutes @ 150°C

### Alternate Cure Schedule

120 minutes @ 125°C

### Cure Pressure

10 to 60 psi

Cure pressure may vary depending on the materials being bonded and their size.

The above cure profiles are guideline recommendations. Cure conditions (time and temperature) may vary based on customers' experience and their application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

## TYPICAL PROPERTIES OF CURED MATERIAL

### Physical Properties

|                                        |                                            |
|----------------------------------------|--------------------------------------------|
| Coefficient of Thermal Expansion, TMA: |                                            |
| Below Tg, ppm/°C                       | 85                                         |
| Above Tg, ppm/°C                       | 195                                        |
| Glass Transition Temperature, DMA, °C  |                                            |
|                                        | 190                                        |
| Storage Modulus, DMA:                  |                                            |
| @ 25 °C                                | N/mm <sup>2</sup> 4,500<br>(psi) (652,669) |
| @ 100 °C                               | N/mm <sup>2</sup> 2,500<br>(psi) (362,594) |
| @ 150 °C                               | N/mm <sup>2</sup> 900<br>(psi) (130,534)   |
| Extractable Ionic Content, @ 100°C:    |                                            |
| Chloride (Cl-)                         | 45                                         |
| Sodium (Na+)                           | 20                                         |
| Potassium (K+)                         | 175                                        |

### Electrical Properties

|                                   |        |
|-----------------------------------|--------|
| Volume Resistivity, ohm-cm @ 25°C | 0.0003 |
|-----------------------------------|--------|

## TYPICAL PERFORMANCE OF CURED MATERIAL

### Miscellaneous

|                                       |                                       |
|---------------------------------------|---------------------------------------|
| Tensile Lap Shear Strength, Al to Al: |                                       |
| @ 25°C                                | N/mm <sup>2</sup> 12<br>(psi) (1,750) |
| @ 150°C                               | N/mm <sup>2</sup> 5.17<br>(psi) (750) |

## GENERAL INFORMATION

For safe handling information on this product, consult the Safety Data Sheet, (SDS).

## DIRECTIONS FOR USE

1. Product is ready to use when it has reached 22°C once removed from frozen or cold temperature storage.
2. Adhesive must be completely used within the product's recommended work life of 3 months.
3. Pressure needs to be applied during cure to promote proper wetting of substrate surfaces. The technique to apply pressure will vary by application and customer preference. For large surface area applications, a load distribution material is recommended between one of the pressure plates and the bonding part in order to equalize the applied pressure over the entire area.
4. Please refer to the Cure Pressure data section of the Technical Data Sheet for the recommended applied pressure range.
5. After fixturing, the parts are then cured at an elevated temperature.
6. The specified temperatures and times refer to the bondline values. It should be noted that large mass assemblies will take longer time to achieve bondline temperatures.
7. LOCTITE ABLESTIK CF 3366 becomes brittle at temperatures below -5°C. If material goes below this temperature, it should be

handled gently. Entire package should be warmed to room temperature before opening. This will minimize the possibility of fracturing in the brittle state or allowing condensation to collect on the product.

#### Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

#### STORAGE:

Store in original, tightly covered containers in clean, dry areas. Storage information may be indicated on the product container labeling. Usable shelf life may vary depending on method of application and storage conditions.

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

#### Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$   
 $\text{kV/mm} \times 25.4 = \text{V/mil}$   
 $\text{mm} / 25.4 = \text{inches}$   
 $\text{N} \times 0.225 = \text{lb}$   
 $\text{N/mm} \times 5.71 = \text{lb/in}$   
 $\text{psi} \times 145 = \text{N/mm}^2$   
 $\text{MPa} = \text{N/mm}^2$   
 $\text{N} \cdot \text{m} \times 8.851 = \text{lb} \cdot \text{in}$   
 $\text{N} \cdot \text{m} \times 0.738 = \text{lb} \cdot \text{ft}$   
 $\text{N} \cdot \text{mm} \times 0.142 = \text{oz} \cdot \text{in}$   
 $\text{mPa} \cdot \text{s} = \text{cP}$

#### Disclaimer

##### Note

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:**

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

**In case products are delivered by Henkel Colombiana S.A.S. the following disclaimer is applicable:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or

any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Corporation Resin Technology Group, Inc., or Henkel Canada, Inc. the following disclaimer is applicable:**

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

#### Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 0.5