



LOCTITE® STYCAST EFF 15

December 2024

PRODUCT DESCRIPTION

LOCTITE® STYCAST EFF 15 provides the following product characteristics:

Technology	Epoxy
Appearance	Light yellow
Cure	Heat cure
Product benefits	• One component • Excellent dielectric properties • Low stress • Low shrinkage • Self-extinguishing
Operating temperature	-65°C to + 175°C
Application	Encapsulant

LOCTITE® STYCAST EFF 15 epoxy based free flowing syntactic foam powder is designed to be able to infiltrate around densely packed components and fill voids in electronic modules. This material exhibits low shrinkage during cure so that little stress is transmitted to the embedded components.

LOCTITE® STYCAST EFF 15 self extinguishes after an external flame is removed.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Density, ASTM D792, g/cm³	0.24
Shelf life @ 10°C, (from date of manufacture), month	8
Flash point - see SDS	

TYPICAL CURING PERFORMANCE

Recommended cure schedule

- 24 hours @ 100°C
- 4 hours @ 120°C
- 2 hours @ 150°C

The above cure profiles are guideline recommendations. These conditions (time and temperature) may vary based on customers' experience and specific application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

TYPICAL PROPERTIES OF CURED MATERIAL

Physical properties

Coefficient of thermal expansion, ASTM D3386, ppm/°C	21
Thermal conductivity, ASTM D-2214, W/(m-K)	0.12

Electrical properties

Dielectric strength, ASTM D149, kV/mm	7.9
Dielectric constant / Dissipation factor , ASTM D150 @ 8.6 GHz	1.38 / 0.006

TYPICAL PERFORMANCE OF CURED MATERIAL

Miscellaneous

Compressive strength, ASTM D695	N/mm² (psi)	1.03 (150)
---------------------------------	-------------	------------

GENERAL INFORMATION

For safe handling information on this product, consult the Safety Data Sheet (SDS).

Directions for use

1. Complete cleaning of the components and substrates should be performed to remove contamination such as dust, moisture, salt and oils which can cause electrical failure, poor adhesion or corrosion in an embedded part.
2. Some separation of components is common during shipping and storage. For this reason, it is recommended that the contents of the shipping container be thoroughly mixed prior to use.
3. LOCTITE® STYCAST EFF 15 has excellent adhesion to a variety of materials. This is of value when the cured foam is to remain in the cavity which it fills.
4. In the event that release from the mold is desired, a coating of paste wax or a silicone mold release such as MOLD RELEASE 122S is recommended.
5. Pour mixture into cavity or mold.
6. Overfill the cavity so there is a mound of material over the opening.
7. Place the container in a vibrating table and lightly vibrate until the level of the powder no longer changes. A spatula may be used to scrape off the excess and create a level surface.
8. One may also vibrate or tap the cavity by hand to fully infiltrate the cavity.
9. The final density of the system may be affected by the efficiency of the vibration method used.
10. The cured LOCTITE® STYCAST EFF 15 can be easily dug out of the cavity with tools to access or replace components. More LOCTITE® STYCAST EFF 15 is then added to the repair area and cured.
11. The cured material can be sealed with a liquid epoxy resin such as LOCTITE® STYCAST 1090 to give the assembly enhanced moisture protection.



Storage

Store product in an unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal storage: 10°C

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Henkel representative.

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on the specifications of this product.

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$
 $\text{kV/mm} \times 25.4 = \text{V/mil}$
 $\text{mm} / 25.4 = \text{inches}$
 $\mu\text{m} / 25.4 = \text{mil}$
 $\text{N} \times 0.225 = \text{lb}$
 $\text{N/mm} \times 5.71 = \text{lb/in}$
 $\text{N/mm}^2 \times 145 = \text{psi}$
 $\text{MPa} \times 145 = \text{psi}$
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$
 $\text{mPa}\cdot\text{s} = \text{cP}$

Disclaimer

The information provided in this Technical data sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical data sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 2