



LOCTITE® EA 9023

September 2021

PRODUCT DESCRIPTION

LOCTITE® EA 9023 provides the following product characteristics:

Technology	Epoxy
Chemical Type	Epoxy
Appearance (Resin)	Off-white
Appearance (Hardener)	Translucent paste
Appearance (Mixed)	Off-white
Components	Two components - requires mixing
Viscosity	Thixotropic
Mix Ratio, by volume - Resin : Hardener	2 : 1
Mix Ratio, by weight - Resin : Hardener	100 : 50
Cure	Room temperature cure after mixing
Application	Potting
Specific Benefits	• Low Adhesion to facilitate removal after a part has been trimmed • Withstands autoclave cycle • Non-Sag • Low Transfer to Carbon Fiber

LOCTITE® EA 9023 is a two-component non-sag, fast setting, industrial grade epoxy potting compound designed for low effort removal from Steel and CFRP tooling. The product withstands the temperature cycling of standard autoclave processes used for composite manufacturing. Once mixed, LOCTITE® EA 9023 cures at room temperature to form a rigid surface. Typical applications include filling grooves in the molds that are used to allow trimming the finished molded part to exact dimensions once the composite is fully cured. It has low adhesion to allow the mold to be rapidly cleaned and fresh material applied.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Part A Properties Resin

Specific Gravity @ 23°C 1.11

Viscosity, Cone & Plate @ 25°C, mPa·s (cP):

Cone & Plate, Spindle CP25-2 @ Shear rate 32,500
10 s⁻¹

Part B Properties Hardener

Specific Gravity @ 23°C 1.11

Viscosity, Cone & Plate @ 25°C, mPa·s (cP):

Cone & Plate, Spindle CP25-2 @ Shear rate 70,000
10 s⁻¹

Mixed Properties

Specific Gravity @ 23°C 1.11

TYPICAL CURING PERFORMANCE

Tested @ 23°C

Working life @ 23 °C, minutes 3.5

Tack Free Time @ 23°C, minutes 4

Gel Time @ 23 °C, minutes 2 to 10

Sag, 100 x 13 x 6 mm Bead, mm 0

TYPICAL PROPERTIES OF CURED MATERIAL

Cured for 16 hours @ 23 °C, plus 2 hours @ 175°C

Physical Properties

Shore Hardness, ISO 868, Durometer A 55

Removal from CFRP Low effort

Removal from steel/composite mold Clean

GENERAL INFORMATION

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.

For safe handling information on this product, consult the Safety Data Sheet (SDS).



DIRECTION FOR USE:

1. Remove surface contaminants such as paint, oxide films, oils, dust, mold release agents and all other surface contaminants.
2. Use gloves to minimize skin contact. DO NOT use solvents for cleaning hands.
3. **Dual Cartridges:** To begin using a new cartridge, remove cartridge cap and dispense a small amount of adhesive, making sure both parts A&B are extruding. Attach mix nozzle and dispense approximately 25 to 50 mm, before applying onto part to be bonded. Partially used cartridges can be stored with the mixing nozzle attached. To reuse, remove and discard old nozzle, attach the new nozzle, dispense approximately 25 to 50mm, before applying onto part to be bonded.

Hand Mixing: Combine Part A & Part B in the correct ratio and mix thoroughly. Be sure to scrape both the sides and bottom of mixing container. Mix for approximately 15 seconds after uniform color is obtained. Heat build-up during or after mixing is normal. Do not mix quantities greater than 0.02 kg as excessive exotherm or heat buildup will develop. Mixing smaller amounts will minimize heat build-up

Bulk Containers: Normally material is dispensed through volumetric metered mixing equipment, attached to static mix nozzles. It may also be mixed by weight or volume as described above.

4. Application to the substrates should be made within 5 minutes. Larger quantities and/or higher temperatures will reduce this working time.
5. Allow to cure. Higher temperatures will speed up curing.
6. Excessive uncured adhesive can be cleaned up with ketone type solvents.

STORAGE

Store product in the unopened container in a dry location. Storage information is indicated on the product container labeling.

Optimal Storage: 8 to 21°C. Storage below 8°C or above 28°C can adversely affect product properties.

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Henkel Representative.

PRODUCT SPECIFICATION

The technical data contained herein are intended as reference only and are not considered specifications for the product. Product specifications are located on the Certificate of Analysis or please contact Henkel representative.

APPROVAL AND CERTIFICATE

Please contact Henkel representative for related approval or certificate of this product.

DATA RANGES

The data contained herein may be reported as a typical value. Values are based on actual test data and are verified on a periodic basis.

Temperature/Humidity Ranges: 23°C / 50% RH = 23±2°C / 50±5% RH

Conversions

$$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$$

$$\text{kV/mm} \times 25.4 = \text{V/mil}$$

$$\text{mm} / 25.4 = \text{inches}$$

$$\mu\text{m} / 25.4 = \text{mil}$$

$$\text{N} \times 0.225 = \text{lb}$$

$$\text{N/mm} \times 5.71 = \text{lb/in}$$

$$\text{N/mm}^2 \times 145 = \text{psi}$$

$$\text{MPa} \times 145 = \text{psi}$$

$$\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$$

$$\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$$

$$\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$$

$$\text{mPa}\cdot\text{s} = \text{cP}$$

Disclaimer

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 1