

**LITHIUM CELLS OR BATTERIES TEST SUMMARY
IN ACCORDANCE WITH SUB-SECTION 38.3
OF MANUAL OF TEST AND CRITERIA**

BATTERY TRANSPORTION INFORMATION

Name of cell, battery or product manufacturer, as applicable: Item Number : CR2032 Item Name : CR2032 Item Description : Lithium Metal Battery Cell	Cell, battery or product manufacturer's contact information to include address, phone number, email address and website for more information: Tohoku Murata Manufacturing Co., Ltd. 1-1 Shimosugishita, Takakura, Hiwada-machi, Koriyama-shi, Fukushima, 963-0531 Japan Phone: +81-24-955-7854 e-mail: tmm-qa-compliance@murata.com Website: https://www.murata.com/en-global/group/tohokumurata	
Name of the test laboratory to include address, phone number, email address and website for more information: Tohoku Murata Manufacturing Co., Ltd. 1-1 Shimosugishita, Takakura, Hiwada-machi, Koriyama-shi, Fukushima, 963-0531 Japan Phone: +81-24-955-7854 e-mail: tmm-qa-compliance@murata.com Website: https://www.murata.com/en-global/group/tohokumurata	A unique test report identification number: UN38.3-CR1220REV	Date of the test report: 15-Jun-23
Description of cell or battery to include at a minimum: Lithium ion or Lithium metal cell or battery; Mass; Watt-hour rating, or lithium content; Physical description of the cell/battery; and Model Cell/battery Type : Lithium Metal Cell or Battery : Cell Cell or Battery Weight : 3.1 g LC or W/h rating : 0.06 g Physical description : Lithium Metal Battery Cell (Coin shaped)	List of tests conducted and results (i.e., pass/fail): Test T.1: Altitude Simulation : Pass Test T.2: Thermal Test : Pass Test T.3: Vibration : Pass Test T.4: Shock : Pass Test T.5: External short circuit : Pass Test T.6: Impact : Pass Test T.7: Overcharge : Not applicable Test T.8: Forced discharge : Pass Testing additional comments:	
Reference to assembled battery testing requirements, if applicable (i.e., 38.3.3;(f) and 38.3.3;(g): Not Applicable	Reference to the revised edition of the Manual of Test and Criteria used and to amendments thereto, if any: Revision 7	

PRODUCT CLASSIFICATION FOR TRANSPORT (According to UN - DGP)

UN Classification: UN3090	Proper Shipping Name: Lithium Metal Batteries
Signature with name and title of signatory as an indication of the validity of information provided: Yukiko Haraguchi Tohoku Quality Assurance Group Senior Manager <i>Yukiko Haraguchi</i>	This document remains valid as long as no changes, modification, or additions are made to the model(s) described in this document, after being transported from a Tohoku Murata Manufacturing. The model(s) has (have) been classified according to the applicable transport regulations and the UN Manual of Tests and Criteria as of the date of the certification, The model(s) must be packed, labeled, and documented according to country and other international regulations for transportation.
Date document was generated: 15-Jun-23	

For product quotations and sales inquiries, please contact the dedicated form on the Murata Manufacturing website.
 Contact to: <https://www.murata.com/en-global/contactform>

Phone: +81 24 955 7834 / Fax: +81 24 958 5827

1 of 8 Page

Date: June 15, 2023

- 組電池／Battery(Pack) (セル構成／Composition of cell :)

- Murata Product Name CR2032

- 4.
- 定格/Rated

5. 類似機種及び試験結果／Similar Model and Test Result

梱包試験実施日／Tested Date for Package : 2015/12/17~2015/12/25

確認した結果であることを証明いたします。

We, Tohoku Murata Manufacturing Co., Ltd., hereby certify that above results are confirmed in accordance with the Manual of Tests and Criteria of the UN Recommendations on the Transport of Dangerous Goods, 7th revised edition, Part III, subsection 38.3.

- ・ 類似機種に対して、正極、負極、電解液質量はいずれも20%以内もしくは0.1g以内の変化率を証明します。

We certify the mass ratios of the subject model to the similar model are within 20% or 0.1g for Cathode, Anode, and Electrolyte.

負極質量比／Anode Mass Ratio = 110%、電解液質量／Electrolyte Mass Ratio = 106%

Hideaki Takahashi
Quality Assurance Department
Tohoku Murata Manufacturing Co., Ltd.

QMJ-19-01-06-F005. 改定2021/01/06

Tohoku Murata Manufacturing Co., Ltd.
1-1 Shimosugishita, Takakura, Hiwada-machi,
Koriyama-shi, Fukushima 963-0531 JAPAN
Phone: +81 24 955 7835 / Fax: +81 24 958 5827

No:UN38.3-CR2032 REV
Date June 15, 2023
Page : 2 of 9 Page

A : Checklist for Judging New Type Cell or not

When there is no change in all items, it is NOT considered to be a New Type Cell.

(Change ⇒ ○、No change ⇒ —)

Battery Pack Model: ○○○○○○ Component Cell Model: ◎◎◎◎◎

Check item	The element which is given influence	Presence of change
Safety parts and mechanical components	Are the safety parts and mechanical components of this cell the same as those of the test completion cell?	—
Cathode material system	Is cathode material system of this cell the same as that of the test completion cell?	—
Anode material system	Is anode material system of this cell the same as that of the test completion cell?	—
Electrolyte material system	Is electrolyte material system of this cell the same as that of the test completion cell?	—
Mass of cathode material	Is mass difference of the design center of each cell concerning cathode less than 20%?	—
Mass of anode material	Is mass difference of the design center of each cell concerning anode less than 20%?	—
Mass of electrolyte	Is mass difference of the design center of each cell concerning electrolyte less than 20%?	—
Judgment result	New Type or not	Not new

Tohoku Murata Manufacturing Co., Ltd.
1-1 Shimosugishita, Takakura, Hiwada-machi,
Koriyama-shi, Fukushima 963-0531 JAPAN
Phone: +81 24 955 7835 / Fax: +81 24 958 5827

No:UN38.3-CR2032 REV
Date June 15, 2023
Page : 3 of 9 Page

B: Checklist for Judging New Type Battery or not

Confirmation of presence of change in "The element which is given influence"

(Change ⇒ ○、No change ⇒ —)

When there is no change in all items, it is NOT considered to be a New Type Battery.

Battery Pack Model: ○○○○○○ Component Cell Model: ◎◎◎◎◎

Test Item (Function)	The element which is given influence	Presence of change
T1: Altitude Simulation (Decompression load)	• Crimped part, Gasket (Cell) • Gas Release Vent, Cell Case (Cell) • Pack (Plastic) Case • Holding Member (Insulator, Insulation Tape, Both Sides Tape) • Coating materials	—
T2: Thermal Shock (Repetition of high temp. and low temp.)	• Crimped part, Gasket (Cell) • Gas Release Vent, Cell Case (Cell) • Finished state of Wound Electrodes (Cell) • Pack (Plastic) Case • Holding Member (Insulator, Insulation Tape, Both Sides Tape) • Coating materials	—
T3: Vibration (Vibration load)	• Finished state of Wound Electrodes (Cell) • Electric wiring member • Electronic Parts on a circuit board • Cell Holding Member (Adhesive, Both Sides Tape, Lib of Plastic Case)	—
T4: Shock (Shock load)	• Wiring Member • Electronic Parts on a circuit board • Cell Holding Member (Adhesive, Both Sides Tape, Lib of Plastic Case) • Finished state of Wound Electrodes (Cell)	—
T5: External Short Circuit (Short current)	• Over-voltage Protection • Current Control Device • Safety Device of cell (Cell) • Lead Tab	—
T6(Cell): Impact (Crash load)	• Separator (Cell) • Insulation State in a cell (Cell)	—
T7(Pack): Overcharge (Charge load)	• Overcharge Protection • Thermal Device • Safety Device of cell (Cell)	—
T8(Cell): Forced Discharge (Over discharge load)	• Finished state of Wound Electrodes (Cell)	—
Judgment result	New Type or not	Not new

機種名 / Murata Model Name		CR2032NonHL(Made in Indonesia)						
試験場所 / Test Company		株式会社 東北村田製作所 郡山事業所						
住所 / Address		〒963-0531 福島県郡山市日和田町高倉下杉下1-1			電話 / Tel.		+81-24-958-3811	
試験室 / Test Room		安全性試験室 / 野外試験室			試験期間 / Test Dates			
判定基準 / Criterion		UN Manual of Tests and Criteria 7th revised edition, Part Ⅲ, sub-section 38.3						
試験名称 / Test Name		T1:高度シミュレーション試験 Altitude Simulation						
番号 No.	サンプル状態 Conditions	試験前 / Before		試験後 / After		質量減少率 / Mass Loss <0.2%以下>	OCV維持率 / Residual OCV 90%以上	現象 / Occurrence
		mass (g)	OCV (V)	mass (g)	OCV (V)			
1	未放電 / Undischarged	3.044	3.248	3.044	3.249	-0.01	100.0	N
2		3.031	3.236	3.031	3.236	0.00	100.0	N
3		3.073	3.247	3.073	3.247	0.00	100.0	N
4		3.025	3.257	3.025	3.257	-0.01	100.0	N
5		3.037	3.244	3.037	3.244	0.00	100.0	N
6		3.031	3.244	3.031	3.243	0.00	100.0	N
7		3.042	3.250	3.042	3.249	0.00	100.0	N
8		3.058	3.245	3.057	3.245	0.01	100.0	N
9		3.051	3.239	3.050	3.239	0.00	100.0	N
10		3.062	3.246	3.062	3.246	0.00	100.0	N
11	完全放電 / Fully discharged	3.028		3.028		0.00		N
12		3.059		3.059		-0.01		N
13		3.051		3.051		0.00		N
14		3.059		3.059		-0.01		N
15		3.052		3.052		0.00		N
16		3.051		3.051		0.00		N
17		3.051		3.051		0.00		N
18		3.034		3.034		0.00		N
19		3.066		3.067		0.00		N
20		3.064		3.065		0.00		N
試験名称 / Test Name		T2:温度試験 Thermal						
番号 No.	サンプル状態 Conditions	試験前 / Before		試験後 / After		質量減少率 / Mass Loss <0.2%以下>	OCV維持率 / Residual OCV 90%以上	現象 / Occurrence
		mass (g)	OCV (V)	mass (g)	OCV (V)			
1	未放電 / Undischarged	3.044	3.249	3.044	3.256	0.01	100.2	N
2		3.031	3.236	3.031	3.249	0.01	100.4	N
3		3.073	3.247	3.073	3.255	0.01	100.2	N
4		3.025	3.257	3.025	3.263	0.01	100.2	N
5		3.037	3.244	3.037	3.252	0.01	100.2	N
6		3.031	3.243	3.031	3.253	0.01	100.3	N
7		3.042	3.249	3.042	3.259	0.01	100.3	N
8		3.057	3.245	3.057	3.256	0.01	100.3	N
9		3.050	3.239	3.050	3.250	0.01	100.3	N
10		3.062	3.246	3.062	3.255	0.01	100.3	N
11	完全放電 / Fully discharged	3.028		3.027		0.01		N
12		3.059		3.059		0.01		N
13		3.051		3.051		0.00		N
14		3.059		3.058		0.01		N
15		3.052		3.052		0.01		N
16		3.051		3.051		0.01		N
17		3.051		3.051		0.01		N
18		3.034		3.034		0.01		N
19		3.067		3.066		0.01		N
20		3.065		3.064		0.01		N
質量減少率 / Mass Loss (%)		□ 電池質量 < 1g: 0.5%以下 ■ 1g ≤ 電池質量 ≤ 75g: 0.2%以下 □ 75g < 電池質量 : 0.1%以下						
【現象 / Occurrence】		破断: R <Rupture> 発火: F <Fire> 破裂: D <Disassembly> 弁作動: V <Venting> 漏液: L <Leakage> 異常なし: N <No rupture, No fire, No disassembly, No venting, No leakage>						

試験名称 / Test Name		T3:振動試験 Vibration						
番号 No.	サンプル状態 Conditions	試験前 / Before		試験後 / After		質量減少率 / Mass Loss <0.2%以下>	OCV維持率 / Residual OCV 90%以上	現象 / Occurrence
		mass (g)	OCV (V)	mass (g)	OCV (V)			
1	未放電 / Undischarged	3.044	3.256	3.044	3.264	0.01	100.2	N
2		3.031	3.249	3.031	3.257	0.00	100.2	N
3		3.073	3.255	3.073	3.264	0.00	100.3	N
4		3.025	3.263	3.025	3.271	0.00	100.3	N
5		3.037	3.252	3.037	3.261	0.00	100.3	N
6		3.031	3.253	3.031	3.261	0.00	100.2	N
7		3.042	3.259	3.042	3.267	0.00	100.2	N
8		3.057	3.256	3.057	3.262	0.00	100.2	N
9		3.050	3.250	3.050	3.259	0.00	100.3	N
10		3.062	3.255	3.062	3.263	0.01	100.2	N
11	完全放電 / Fully discharged	3.027		3.027		0.00		N
12		3.059		3.059		0.00		N
13		3.051		3.051		-0.01		N
14		3.058		3.059		0.00		N
15		3.052		3.052		0.00		N
16		3.051		3.051		0.00		N
17		3.051		3.051		0.00		N
18		3.034		3.034		0.00		N
19		3.066		3.066		0.00		N
20		3.064		3.064		0.00		N
試験名称 / Test Name		T4:衝撃試験 Shock						
番号 No.	サンプル状態 Conditions	試験前 / Before		試験後 / After		質量減少率 / Mass Loss <0.2%以下>	OCV維持率 / Residual OCV 90%以上	現象 / Occurrence
		mass (g)	OCV (V)	mass (g)	OCV (V)			
1	未放電 / Undischarged	3.044	3.264	3.044	3.263	0.00	100.0	N
2		3.031	3.257	3.030	3.256	0.01	100.0	N
3		3.073	3.264	3.073	3.264	0.00	100.0	N
4		3.025	3.271	3.025	3.271	0.00	100.0	N
5		3.037	3.261	3.037	3.259	0.00	100.0	N
6		3.031	3.261	3.031	3.259	0.00	100.0	N
7		3.042	3.267	3.042	3.265	0.00	100.0	N
8		3.057	3.262	3.057	3.262	0.00	100.0	N
9		3.050	3.259	3.050	3.258	0.01	100.0	N
10		3.062	3.263	3.062	3.262	-0.01	100.0	N
11	完全放電 / Fully discharged	3.027		3.027		0.00		N
12		3.059		3.059		0.00		N
13		3.051		3.051		0.01		N
14		3.059		3.059		0.00		N
15		3.052		3.052		0.00		N
16		3.051		3.051		0.00		N
17		3.051		3.051		0.00		N
18		3.034		3.034		0.00		N
19		3.066		3.066		0.00		N
20		3.064		3.064		0.00		N
質量減少率 / Mass Loss (%)		☐ 電池質量 < 1g: 0.5%以下 ■ 1g ≤ 電池質量 ≤ 75g: 0.2%以下 ☐ 75g < 電池質量 : 0.1%以下						
【現象 / Occurrence】		破断: R <Rupture> 発火: F <Fire> 破裂: D <Disassembly> 弁作動: V <Venting> 漏液: L <Leakage> 異常なし: N <No rupture, No fire, No disassembly, No venting, No leakage>						

国連勧告試験 結果 3

Test Result of UN Recommendations Part 3

No.UN38.3-CR2032
 DATE: June 15, 2023
 PAGE: 6 of 9 page

試験名称 / Test Name		T5:外部短絡試験 External Short Circuit	
番号 No.	サンプル状態 Conditions	最大表面温度 / Max. Surface Temperature 170℃≧	現象確認/ Occurrence
1	未放電 / Undischarged	63℃	N
2		63℃	N
3		62℃	N
4		62℃	N
5		63℃	N
6		63℃	N
7		63℃	N
8		63℃	N
9		63℃	N
10		63℃	N
11	完全放電 / Fully discharged	58℃	N
12		58℃	N
13		58℃	N
14		58℃	N
15		57℃	N
16		58℃	N
17		58℃	N
18		58℃	N
19		58℃	N
20		58℃	N
現象 / Occurrence		破断 : R <Rupture> 発火 : F <Fire> 破裂 : D <Disassembly> 異常なし : N <No rupture, No fire, No disassembly>	

試験名称 / Test Name		T6: 圧壊試験 Crash	
番号 No.	サンプル状態 Conditions	最大表面温度 / Max. Surface Temperature 170℃≥	現象確認/ Occurrence
1	未放電 / Undischarged	170℃以下	N
2		170℃以下	N
3		170℃以下	N
4		170℃以下	N
5		170℃以下	N
6	完全放電 / Fully discharged	170℃以下	N
7		170℃以下	N
8		170℃以下	N
9		170℃以下	N
10		170℃以下	N

試験名称 / Test Name	T7: 過充電 Overcharge
対象外 / Not Applicable	

試験名称 / Test Name		T8: 強制放電 Forced Discharge
番号 No.	サンプル状態 Conditions	現象確認/ Occurrence
1	完全放電 / Fully discharged	N
2		N
3		N
4		N
5		N
6		N
7		N
8		N
9		N
10		N
【現象 / Occurrence】		発火: F <Fire> 破裂: D <Disassembly> 異常なし: N <No fire, No disassembly>




国連勸告試験 梱包結果

Test Result of UN Recommendations for Package

No : UN38.3-CR2032
DATE : REV June 15 ,2023
PAGE : 7 of 9 Page

試験場所/ Test Company	株式会社 東北村田製作所/Tohoku Murata Manufacturing Co., Ltd.							
住所/ Address	〒963-0531 福島県郡山市日和田町高倉下杉下1-1 1-1, Shimosugishita, Takakura, Hiwada-machi, Koriyama Fukushima 963-0531 Japan			電話/ Tel	+81-24-958-3811			
試験室/ Test Room	オクト産業(株)評価室/ Industrial Design OCTO	試験期間/ Test Dates	2015/12/17～2015/12/25		試験番号 /Test No	AB – 1512 – 001		
モデル名/ Model Name	CR2032		梱包入り数 /Quantity		700 pcs			
セルタイプ/ Cell Type	CR2032	構成/ Configuration	単セル/ Single Cell	梱包製造地/ Package Location	Indonesia			
包装等級 / Packing Group	等級Ⅱ /Packing Group Number II							
寸法・質量 / Dimensions and Gross Weight	長辺/Length (L)		短辺 /Wide (W)		高さ/Height (H)		質量 /Gross Weight (kg)	
	342 mm		183 mm		150 mm		3.0 kg	

落下試験/Drop Test				
試験設備/ Test equipment	DT-100B			
試験条件/ Test condition	落下高さ /Drop height	1. 2 m	試験結果 /Occurrence	
落下姿勢(方向) / Five (one for each drop) 	1回目の落下試験 The first drop test	底面を水平に/ Flat on the bottom	著しい破損なし/No Leakage, No damage liable to affect safety during transportation	
	2回目の落下試験 The second drop test	天面を水平に / Flat on the top	著しい破損なし/No Leakage, No damage liable to affect safety during transportation	
	3回目の落下試験 The third drop test	長側面を水平に/ Flat on the long side	著しい破損なし/No Leakage, No damage liable to affect safety during transportation	
	4回目の落下試験 The fourth drop test	短側面を水平に/ Flat on the short side	著しい破損なし/No Leakage, No damage liable to affect safety during transportation	
	5回目の落下試験 The fifth drop test	コーナー（角）※/ On a corner	著しい破損なし/No Leakage, No damage liable to affect safety during transportation	
	※容器が最も破損を受ける方向を選択/Use the direction of carton which may have the most serious damage.			
	判定基準/ Criterion	外装容器及び袋の場合、外装容器の最も外側の層に輸送中の安全を脅かすようないかなる破損が生じてはならない。 /On the outmost layer of the exterior container or bag, there shall be no damage which shall badly affect safety during transportation.		判定/ Judgment

積み重ね試験/Stacking Test				
試験条件/ Test condition	No	試験結果 /Occurrence		
3mの想定段数算出/ Equivalent package number stacked up 3m	20段	1	漏洩・破損・歪みなし/ No leakage, No distortion, No deterioration	
試験荷重値算出/ Examination load calculation value	76kg	2	漏洩・破損・歪みなし/ No leakage, No distortion, No deterioration	
試験荷重値/Weight Load	155 kg	3	漏洩・破損・歪みなし/ No leakage, No distortion, No deterioration	
判定基準/ Criterion	試供品は漏洩があつてはならない。試供品は、輸送の安全性を損なうような劣化、又はその強度を減じたり、又は輸送物の積み重ねを不安定にするような歪みが生じてはならない。 No leakage, no deterioration which may affect badly safety transportation, no distortion which may cause unstable stacking.		判定/ Judgment	合格/OK

総合判定

合格/OK


国連勧告試験 梱包結果

Test Result of UN Recommendations for Package

No : UN38.3-CR2032
DATE : REV June 15 ,2023
PAGE : 8 of 9 Page

試験場所/ Test Company	株式会社 東北村田製作所/Tohoku Murata Manufacturing Co., Ltd.					
住所/ Address	〒963-0531 福島県郡山市日和田町高倉下杉下1-1 1-1, Shimosugishita, Takakura, Hiwada-machi, Koriyama Fukushima 963-0531 Japan				電話/ Tel	+81-24-958-3811
試験室/ Test Room	オクト産業(株)評価室/ Industrial Design OCTO	試験期間/ Test Dates	2015/12/17～2015/12/25		試験番号 /Test No	AB – 1512 – 001
モデル名/ Model Name	CR2032		梱包入り数 /Quantity		1400 pcs	
セルタイプ/ Cell Type	CR2032	構成/ Configuration	単セル/ Single Cell	梱包製造地/ Package Location	Indonesia	
包装等級 / Packing Group	等級Ⅱ /Packing Group Number II					
寸法・質量 / Dimensions and Gross Weight	長辺/Length (L)		短辺 /Wide (W)		高さ/Height (H)	
	342 mm		183 mm		150 mm	
					質量 /Gross Weight (kg)	
					5.4 kg	

落下試験/Drop Test

試験設備/ Test equipment	DT-100B		
試験条件/ Test condition	落下高さ /Drop height	1. 2 m	試験結果 /Occurrence
落下姿勢(方向) / Five (one for each drop) 	1回目の落下試験 The first drop test	底面を水平に/ Flat on the bottom	著しい破損なし/No Leakage, No damage liable to affect safety during transportation
	2回目の落下試験 The second drop test	天面を水平に / Flat on the top	著しい破損なし/No Leakage, No damage liable to affect safety during transportation
	3回目の落下試験 The third drop test	長側面を水平に/ Flat on the long side	著しい破損なし/No Leakage, No damage liable to affect safety during transportation
	4回目の落下試験 The fourth drop test	短側面を水平に/ Flat on the short side	著しい破損なし/No Leakage, No damage liable to affect safety during transportation
	5回目の落下試験 The fifth drop test	コーナー（角）※/ On a corner	著しい破損なし/No Leakage, No damage liable to affect safety during transportation
	※容器が最も破損を受ける方向を選択/Use the direction of carton which may have the most serious damage.		
	判定基準/ Criterion	外装容器及び袋の場合、外装容器の最も外側の層に輸送中の安全を脅かすようないかなる破損が生じてはならない。 /On the outmost layer of the exterior container or bag, there shall be no damage which shall badly affect safety during transportation.	判定/ Judgment

積み重ね試験/Stacking Test

試験条件/ Test condition		No	試験結果 /Occurrence	
3mの想定段数算出/ Equivalent package number stacked up 3m		20段	1	漏洩・破損・歪みなし/ No leakage, No distortion, No deterioration
試験荷重値算出/ Examination load calculation value		114kg	2	漏洩・破損・歪みなし/ No leakage, No distortion, No deterioration
試験荷重値/Weight Load		155 kg	3	漏洩・破損・歪みなし/ No leakage, No distortion, No deterioration
判定基準/ Criterion	試供品は漏洩があつてはならない。試供品は、輸送の安全性を損なうような劣化、又はその強度を減じたり、又は輸送物の積重ねを不安定にするような歪みが生じてはならない。 No leakage, no deterioration which may affect badly safety transportation, no distortion which may cause unstable stacking.		判定/ Judgment	合格/OK

総合判定


合格/OK

国連勧告試験 梱包結果

Test Result of UN Recommendations for Package

No : UN38.3-CR2032
DATE : REV June 15,2023
PAGE : 9 of 9 Page

試験場所/ Test Company	株式会社 東北村田製作所/Tohoku Murata Manufacturing Co., Ltd.					
住所/ Address	〒963-0531 福島県郡山市日和田町高倉下杉下1-1 1-1, Shimosugishita, Takakura, Hiwada-machi, Koriyama Fukushima 963-0531 Japan			電話/ Tel	+81-24-958-3811	
試験室/ Test Room	オクト産業(株)評価室/ Industrial Design OCTO	試験期間/ Test Dates	2015/01/14～2015/01/17		試験番号 /Test No	AB – 1501 – 002
モデル名/ Model Name	CR2032		梱包入り数 /Quantity		4000 pcs	
セルタイプ/ Cell Type	CR2032	構成/ Configuration	単セル/ Single Cell	梱包製造地/ Package Location	Indonesia	
包装等級 / Packing Group	等級Ⅱ /Packing Group Number Ⅱ					
寸法・質量 / Dimensions and Gross Weight	長辺/Length (L)	短辺 /Wide (W)	高さ/Height (H)		質量 /Gross Weight (kg)	
	356 mm	353 mm	198 mm		15.2 kg	

落下試験/Drop Test			
試験設備/ Test equipment	DT-100B		
試験条件/ Test condition	落下高さ /Drop height	1 . 2 m	試験結果 /Occurrence
落下姿勢(方向) / Five (one for each drop) 	1回目の落下試験 The first drop test	底面を水平に/ Flat on the bottom	著しい破損なし/No Leakage, No damage liable to affect safety during transportation
	2回目の落下試験 The second drop test	天面を水平に / Flat on the top	著しい破損なし/No Leakage, No damage liable to affect safety during transportation
	3回目の落下試験 The third drop test	長側面を水平に/ Flat on the long side	著しい破損なし/No Leakage, No damage liable to affect safety during transportation
	4回目の落下試験 The fourth drop test	短側面を水平に/ Flat on the short side	著しい破損なし/No Leakage, No damage liable to affect safety during transportation
	5回目の落下試験 The fifth drop test	コーナー（角）※/ On a corner	著しい破損なし/No Leakage, No damage liable to affect safety during transportation
	※容器が最も破損を受ける方向を選択/Use the direction of carton which may have the most serious damage.		
	判定基準/ Criterion	外装容器及び袋の場合、外装容器の最も外側の層に輸送中の安全を脅かすようないかなる破損が生じてはならない。 /On the outmost layer of the exterior container or bag, there shall be no damage which shall badly affect safety during transportation.	判定/ Judgment

積み重ね試験/Stacking Test				
試験条件/ Test condition	No	試験結果 /Occurrence		
3mの想定段数算出/ Equivalent package number stacked up 3m	16段	1	漏洩・破損・歪みなし/ No leakage, No distortion, No deterioration	
試験荷重値算出/ Examination load calculation value	240kg	2	漏洩・破損・歪みなし/ No leakage, No distortion, No deterioration	
試験荷重値/Weight Load	240 kg	3	漏洩・破損・歪みなし/ No leakage, No distortion, No deterioration	
判定基準/ Criterion	試供品は漏洩があってはならない。試供品は、輸送の安全性を損なうような劣化、又はその強度を減じたり、又は輸送物の積み重ねを不安定にするような歪みが生じてはならない。 No leakage, no deterioration which may affect badly safety transportation, no distortion which may cause unstable stacking.		判定/ Judgment	合格/OK

総合判定
合格/OK